

Alumide

High temperature resistant

Metallic appearance

A mix of polyamide powder and aluminium particles producing a strong, stiff thermoplastic with a metallic finish.



Benefits

- High rigidity
- High temperature-resistance
- Multiple finishing options, including grinded, polished, or coated

Applications

- Suitable for wind tunnel tests
- Tool inserts
- Jig manufacture
- Illustrative models



Physical Properties

Colour	Metallic
Type	Aluminium filled SLS

Mechanical Properties

		TEST/ISO
Hardness Shore A/D	76D	DIN 53505
Flexural Modulus (MPa)	3,600	DIN EN ISO178
Tensile Strength (MPa)	48	Din EN ISO527
Tensile Modulus (MPa)	3,800	
Elongation Break (%)	4	
Impact Strength (J/m)	29	DIN EN ISO180
Density (g/cm)	1.36	N/A

Thermal & Specific Properties

Melting Point (°C)	172 – 180	DIN 53736
Heat deflection temperature (°C)	177	ASTM D648
Heat Conductivity [W(mk) ⁻¹]	0.5 – 0.8	Hot wire method

Electrical Properties

Surface Resistance [10V]	3 x 10 ¹² Ω	IEC93
Volume Resistance [10V]	6 x 10 ¹² Ω	
Dielectric Constant (1kHz)	13 ± 438 (100Hz)	
Dielectric loss factor (1kHz)	0.018 ± 0.002	DIN 53483

Call: 028 9070 6940

Email: sales@laserproto.com

Web: www.laserproto.com

[Click here to request a quote](#)

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.