

MED-AMB 10

Biocompatible Rigid

Applications requiring biocompatibility, translucency and/or thermal resistance



Simulating high-temperature plastic, this translucent amber material produces highly accurate parts.

Benefits

- Ultra-high temperature resistant, with temperature resistance of over 100°C
- High rigidity
- Excellent feature resolution and high definition

Applications

- General medical applications requiring biocompatibility, sterilization and/or thermal resistance
- Surgical drill guides, splints
- Parts requiring rigidity with high temperature resistance
 - Fluid handling manifolds
 - Elevated temperature testing
- Parts with high definition details
 - Threaded assemblies
- Visualization and fluid flow models



Physical Properties

Colour	Amber
Type	ABS

Liquid Material

Solid Density (g/cm ³)	1.20
Layer Thickness (mm)	0.05

Mechanical Properties

		TEST/ISO
Tensile Strength (MPa)	69	ASTM D638
Tensile Modulus (MPa)	2760	
Elongation at Break (%)	4	
Flexural Strength (MPa)	111	ASTM D790
Flexural Modulus (MPa)	2810	
Notched Izod Impact Strength (J/m)	18	ASTM D256
Unnotched Izod Impact Strength (J/m)	220	ASTM D4812
Heat Deflection Temperature (°C)		ASTM D648
@ 0.45 MPA	119	
@ 1.82 MPA	94	
Co-efficient of Thermal Expansion (µ/m°C)		ASTM E831
<T _g	84	
>T _g	177	
Glass Transition (T _g)	110°C	ASTM E1640
Shore Hardness	84D	ASTM D2240
Water Absorption (%)	0.26	ASTM D570

Call: 028 9070 6940

Email: sales@laserproto.com

Web: www.laserproto.com

[Click here to request a quote](#)

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.