

## VC 3385

Flame Retardant casting resin with excellent physical properties



### Physical Properties

Colour	Straw Coloured
Material	Polyurethane
Maximum Thickness	15mm

### Mechanical Properties

				TEST/ISO
Hardness	Shore D	@25 °C	85 – 90	BS EN ISO 868
Flexural Strength (MPa)			105 - 115	BS EN ISO 178
Flexural Modulus (MPa)			2250 - 2750	
Tensile Strength (MPa)			80 - 85	BS EN ISO 527
Tensile Modulus (MPa)			1500 - 1900	
Elongation Break (%)			6.0 – 8.0	

### Thermal & Specific Properties

Flame Retardancy	V-0	UL94 3mm Thickness
Heat Distortion Temperature (°C)	65 - 75	TMA
Glass Transition Temperature Standard (°C)	79 - 83	DMA
Glass Transition Temperature Postcure (°C)	97 - 101	

Call: 028 9070 6940

Email: [sales@laserproto.com](mailto:sales@laserproto.com)

Web: [www.laserproto.com](http://www.laserproto.com)

[Click here](#) to request a quote

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.