

Aluminium AlSi10Mg

Light weight with Good Thermal Properties

A high temperature, high performance, Corrosion & Oxidation resistant Nickel-Chromium alloy



Benefits

- High dynamic load bearing capacity
- Good strength and hardness
- Lightweight and heat-resistant

Applications

- Ideal for applications which require a combination of good thermal properties and low weight
- Typically used for cast parts with thin walls and complex capacity
- Automotive, aerospace and automation
- Housings, engine parts and production tools



Physical Properties

Colour	Grey
Type	Aluminium

Mechanical Properties

	Heat Treated ²	
	Horizontal	Vertical
Ultimate tensile strength, R _m	340 MPa	350 MPa
Yield Strength, R _{p0.2}	220 MPa	225 MPa
Elongation at break, A	12%	9%
Density (g/cm ³)	2.59-2.65	

Hardness

Hardness (HBW)	119 ± 5
----------------	---------

¹ The numbers are typical values and are determined from samples with horizontal and vertical orientation.

² Tensile testing according to ISO 6892-1 B10, proportional test pieces, diameter of the neck area 5 mm (0.2 inch), original gauge length 25 mm (1 inch).

³ Stress relieve: anneal for 90 minutes at 270 °C (518 °F). Oven type & configuration may have impact on the mechanical properties; longer holding time and higher temperature can lead to decreased strength and in-creased elongation properties and vice versa. Values given in above table were obtained by inserting parts to preheated oven; annealing time calculation started when part temperature reached 6 °C below target temperature; maximum overheating was < 5°C.

Material composition

Element	Indicative Value (%)
Al	Balance
Si	9.0 – 11.0
Fe	0.55
Cu	0.05
Mn	0.45
Mg	0.25 – 0.45
Ni	0.05
Zn	0.10
Pb	0.05
Sn	0.05
Ti	0.15

Call: 028 9070 6940

Email: sales@laserproto.com

Web: www.laserproto.com

[Click here](#) to request a quote

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.