

# High Temp 150C FR Black

## High Temperature

Applications demanding high heat deflection temperature

Simulating black ABS/PC, this UL94 V0 rated flame-retardant material has >150°C heat deflection temperature.



## Benefits

- Self-extinguishing/flame-retardant and halogen-free
- Injection moulded-like surface quality
- Extremely good long-term environmental stability

## Applications

- Printed circuit board covers
- Electrical and under-hood housings requiring UL94 V0 rating
- Rigid covers, hangers, and brackets
- Small FAR 25/23.853 in-cabin parts
- Flame retardant parts for trains and buses



## Physical Properties

Colour	Black
Type	ABS/PC

## Mechanical Properties

		TEST/ISO
Solid Density	1.29g/cm <sup>3</sup>	ASTM D792
Tensile Strength (MPa)	58	ASTM D638
Tensile Modulus (MPa)	2600	
Elongation at Break (%)	4	
Elongation at Yield (%)	N/A	
Flexural Strength (MPa)	100	ASTM D790
Flexural Modulus (MPa)	2900	
Notched Izod Impact Strength (J/m)	10	ASTM D256
Unnotched Izod Impact Strength (J/m)	50	ASTM D4812
<b>Heat Deflection Temperature (°C)</b>		
@ 0.455 MPA	>150°C	ASTM D648
@ 1.82 MPA	89°C	
Shore Hardness	85D	ASTM D2240
24hr Water Absorption (%)	0.26	ASTM D570

## Electrical

Dielectric Strength (kV/mm) @3mm	15.2	ASTM D149
Dielectric Constant @ 1MHz	3.19	ASTM D150
Dissipation Factor @ 1MHz	0.029	
Volume Resistivity (Ω·cm)	3.36X10 <sup>15</sup>	ASTM D257

Call: 028 9070 6940

Email: [sales@laserproto.com](mailto:sales@laserproto.com)

Web: [www.laserproto.com](http://www.laserproto.com)

[Click here](#) to request a quote

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.