

F141

40 Shore A Elastomer

Physical Properties	
Colour	Translucent Amber
Pigmentable	Yes

Mechanical Properties		
		TEST/ISO
Hardness Shore A/D	40A ±5	ASTM D2240-04e1
Tensile Strength (psi)	919	ASTM D412-98a
Tensile Modulus (psi)	203	
Elongation Break (%)	670	
Tear Strength (pli)	102	ASTM D624-00e1

Electrical Properties		
Dielectric Constant, 1MHz	5.332	ASTM D150-87
Dissipation Factor, 1MHz	0.064	