

PR 751

High heat resistance. Simulates PEEK/PPS

Physical Properties		
Colour	Black	
Pigmentable	No	

Mechanical Properties			
Hardness	Shore A/D	81D	TEST/ISO
			868
Flexural Strength (MPa)		90	178
Flexural Modulus (MPa)		2000	
Tensile Strength (MPa)		80	527
Elongation Break (%)		8	527

Thermal & Specific Properties		
Heat Deflection Temperature (°C)	150	75 Ae