

UPX 8400

Variable hardness from 30-95 A Shore – ideal for rubber like parts

Physical Properties	
Colour	Off White
Pigmentable	Yes

Mechanical Properties		
@ Shore 95A		
		TEST /ISO
Tensile Strength (MPa)	16.20	37
Elongation Break (%)	390	
Tear Strength (MPa)	22.20	34

@ Shore 65A		
Tensile Strength (MPa)	6.70	37
Elongation Break (%)	410	
Tear Strength (MPa)	11.50	34

@ Shore 40A		
Tensile Strength (MPa)	3.6	37
Elongation Break (%)	430	
Tear Strength (MPa)	6.3	34

@ Shore 30A		
Tensile Strength (MPa)	2.1	37
Elongation Break (%)	550	
Tear Strength (MPa)	3.75	34

[Click here](#) to request a quote
or phone us on 028 9070 6940