

VC 3342

Water clear UV Stable PU Casting Resin

Physical Properties			
Colour	Water clear		
Pigmentable	Yes		

Mechanical Properties			
Hardness	Shore A/D	@25 °C	TEST /ISO
			55 -60A
Tensile Strength (MPa)			1.1 – 1.3
Elongation Break (%)			65-85
			BS 2782
			R 527