

VC 3398

Simulates ABS/PC - Water clear thermoplastics.

Physical Properties	
Colour	Clear
Pigmentable	Yes

Mechanical Properties			
Hardness	Shore A/D	@ 25°C	85-90D
Flexural Strength (MPa)			70-75
Flexural Modulus (MPa)			1500-2000
Tensile Strength (MPa)			58-63
Elongation Break (%)			6-7
Linear Shrinkage (%)			<0.4*
			Standard
			BS 2782
			500 x 50 x 10mm

Thermal & Specific Properties	
Heat Deflection Temperature (°C)	130-140

* Shrinkage value quoted as guide only.