

## 2185

Simulates PE/PP – High thermal resistance

Physical Properties	
Colour	Black
Pigmentable	No

Mechanical Properties			
Hardness	Shore A/D	@ 23°C	<b>80D</b>
			<b>TEST/ISO</b>
			868
Flexural Strength (MPa)			<b>60</b>
Flexural Modulus (MPa)			<b>1190</b>
Tensile Strength (MPa)			<b>45</b>
Tensile Modulus (MPa)			<b>1300</b>
Izod Impact (Kj/m <sup>2</sup> )			<b>8.3</b>
Elongation Break (%)			<b>33.8</b>

Thermal & Specific Properties		
Glass Transition Temperature (°C)	<b>150</b>	BS874
Heat Deflection Temperature (°C) (Test piece 110 x 12.7 x 6.4mm)	<b>110-130</b>	

[Click here](#) to request a quote  
or phone us on 028 9070 6940