

F180

Similar to ABS – Good Impact Resistance with low shrinkage

Physical Properties

Colour	Beige
Pigmentable	Colour Dependent

Mechanical Properties

			TEST/ISO
Hardness	Shore A/D	@ 23°C	74D
Flexural Strength (MPa)			34
Charpy Impact (Kj/m ²)			18
Elongation Break (%)			15
Linear Shrinkage on:			
200 x 70 x 3 mm sample			5*
1000 x 50 x 10mm sample			5*

Thermal & Specific Properties

Glass transition temperature (°C)	98	11359-2
-----------------------------------	-----------	----------------

*Shrinkage value quoted as guide only

Call: 028 9070 6940

Email: sales@laserproto.com

Web: www.laserproto.com

[Click here to request a quote](#)

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.