

PX205

Unbreakable Hinge Effect – Simulates HDPE

Physical Properties

Colour	Cream to Dark Beige
Pigmentable	Colour Dependent

Mechanical Properties

				TEST/ISO
Hardness	Shore A/D	@ 23°C	70D	ISO 868 : 2003
Flexural Strength (MPa)			30	ISO 178 : 2001
Flexural Modulus (MPa)			500	
Tensile Strength (MPa)			25	ISO 527 : 1993
Tensile Modulus (MPa)			530	
Elongation Break (%)			100	

Thermal & Specific Properties

Glass transition temperature (°C)	90-100	TMA Mettler
Heat deflection temperature (°C)	55	ISO 75 Ae-93

*Shrinkage value quoted as guide only

Call: 028 9070 6940

Email: sales@laserproto.com

Web: www.laserproto.com

[Click here to request a quote](#)

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.