

VC 3392

High temperature casting resin with excellent impact and chemical resistance



Physical Properties

Colour	Amber
Pigmentable	Yes

Mechanical Properties

			TEST/ISO
Hardness Shore A/D	@25 °C	80 - 85D	BS 2782
Flexural Strength (MPa)		80 - 90	
Flexural Modulus (MPa)		1800 - 2200	
Tensile Strength (MPa)		65 - 70	
Elongation Break (%)		7 - 10	

Thermal & Specific Properties

Chemical Resistance (Petrol)	Excellent
Heat deflection temperature (°C)	120

Call: 028 9070 6940

Email: sales@laserproto.com

Web: www.laserproto.com

[Click here](#) to request a quote

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.