

VC 3398

Simulates ABS/PC - Water clear thermoplastics.



Physical Properties

Colour	Clear
Pigmentable	Yes

Mechanical Properties

				TEST/ISO
Hardness	Shore A/D	@ 25°C	85-90D	BS 2782
Flexural Strength (MPa)			70-75	
Flexural Modulus (MPa)			1500-2000	
Tensile Strength (MPa)			58-63	
Elongation Break (%)			6-7	
Linear Shrinkage (%)			<0.4*	500 x 50 x 10mm

Thermal & Specific Properties

Heat Deflection Temperature (°C)	130-140
----------------------------------	----------------

* Shrinkage value quoted as guide only.

Call: 028 9070 6940

Email: sales@laserproto.com

Web: www.laserproto.com

[Click here to request a quote](#)

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.