

3175

Flexible Rubber ideal for seals & gaskets



Physical Properties

Colour	Translucent Yellow
Pigmentable	Colour Dependent

Mechanical Properties

			TEST/ISO	
Hardness	Shore A/D	@ 23°C	75A	868
		@ 60°C	72A	
Tensile Strength (N/mm ²)			12	R527
Tensile Modulus (N/mm ²)			3.5	
Elongation Break (%)			450	
Tear Strength (N/mm ²)			40	

Thermal & Specific Properties

Glass Transition Temperature Tg (°C)	-	-
Heat Deflection Temperature (°C) (Test piece 110 x 12.7 x 6.4mm)	-	-

Call: 028 9070 6940

Email: sales@laserproto.com

Web: www.laserproto.com

[Click here to request a quote](#)

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.