

UPX VC3300

Variable hardness from 35-95 A Shore – ideal for rubber like parts



Physical Properties

Colour	Off White
Pigmentable	Yes

Mechanical Properties

@ Shore 95A		TEST/ISO
Tensile Strength (MPa)	9.5 – 11.5	37
Elongation Break (%)	200 - 300	

@ Shore 75A		TEST/ISO
Tensile Strength (MPa)	7.5 – 9.5	37
Elongation Break (%)	400 - 500	

@ Shore 55A		TEST/ISO
Tensile Strength (MPa)	4.0 – 6.0	37
Elongation Break (%)	700 - 800	

@ Shore 35A		TEST/ISO
Tensile Strength (MPa)	1.5 – 3.5	37
Elongation Break (%)	900 - 1100	

Call: 028 9070 6940

Email: sales@laserproto.com

Web: www.laserproto.com

[Click here to request a quote](#)

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.