

CL31AL Aluminium Alloy

Similar Properties to 6082

Light, Functional, Heat Resistant



Applications

Material is used for manufacturing

- lightweight prototypes
- Unique or series production parts
- Automotive parts
- Aerospace parts



Physical Properties

Colour	Grey
Type	Aluminium

Mechanical Properties

	Heat Treatment
Yield Strength R_e^1	170 – 220 N/mm ²
Tensile Strength R_m^1	310 – 325 N/mm ²
Elongation A^1	2 – 3 %
Young's modulus ²	Approx. $75 \cdot 10^3$ N/mm ²
Thermal Conductivity λ^2	120 – 180 W/mK
Coefficient of thermal expansion (at rt) ²	$20 \cdot 10^{-6}$ K ⁻¹

¹ Tensile test according to DIN EN 50125 at 20°C

² Specification according to the material manufacturer's data sheet

Material Composition

Component	CL 30AL Indicative Value (%)	CL 31AL Indicative Value (%)
Al	Balance	Balance
Si	10,5 – 13,5	9,0 – 11,0
Mg	0 – 0,05	0,20 – 0,45
Fe	0 – 0,55	0 – 0,55
Mn	0 – 0,35	0 – 0,45
Ti	0 – 0,15	0 – 0,15
Cu	0 – 0,05	0 – 0,10
Zn	0 – 0,10	0 – 0,10
C	0 – 0,05	0 – 0,05
Ni	0 – 0,05	0 – 0,05
Pb	0 – 0,05	0 – 0,05
Sn	0 – 0,05	0 – 0,05

Call: 028 9070 6940

Email: sales@laserproto.com

Web: www.laserproto.com

[Click here to request a quote](#)

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.