

MED-WHT 10

Biocompatible, High Temperature

A rigid white material for applications requiring biocompatibility and / or thermal resistance. It provides beautiful parts that can be sterilized and tested at temperatures over 100 deg C



Applications

- General medical applications requiring biocompatibility, sterilization and/or thermal resistance
- Surgical drill guides, splints
- Bone models
- Parts requiring rigidity with high temperature and/or water resistance
- Parts with high definition details



Physical Properties

Colour	White
Type	ABS

Liquid Material

Solid Density (g/cm ³)	1.18
Layer Thickness (mm)	0.05

Mechanical Properties

		TEST/ISO
Tensile Strength, Ultimate (MPa)	60	ASTM D638
Tensile Strength, at Yield (MPa)	60	
Tensile Modulus (MPa)	3090	
Elongation at Break (%)	3	
Elongation at Yield (%)		
Flexural Strength (MPa)	112	ASTM D790
Flexural Modulus (MPa)	3290	
Notched Izod Impact Strength (J/m)	17	ASTM D256
Unnotched Izod Impact Strength (J/m)	91	ASTM D4812
Heat Deflection Temperature (°C)		ASTM D648
@ 0.45 MPa	102	
@ 1.82 MPa	79	
Co-efficient of Thermal Expansion (ppm/°C)		ASTM E831
<T _g	83	
>T _g	154	
Glass Transition (T _g)	102°C	ASTM E1640
Shore Hardness	84D	ASTM D2240
Water Absorption (%)	0.25	ASTM D570

Call: 028 9070 6940

Email: sales@laserproto.com

Web: www.laserproto.com

[Click here to request a quote](#)

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.