

FLEX BLK 10

Production Flexible

Flexible material for the production of exceptionally durable polypropylene-like parts



Applications

- Functional assemblies and prototypes
 - Automotive styling parts
 - Consumer goods and electronic components
 - Snap fit assemblies
 - Containers and enclosures
 - Product design
- Master patterns for RTV/silicone molding
- Replacement of short-run cast urethane production parts
- Concept and marketing models



Physical Properties

Colour	Black
Type	Polypropylene

Liquid Material

Solid Density (@ 25°C)	1.15g/cm ³
Layer Thickness (mm)	0.10

Mechanical Properties

		TEST/ISO
Tensile Strength, Ultimate (MPa)	46	ASTM D638
Tensile Strength, at Yield (MPa)	37	
Tensile Modulus (MPa)	1400	
Elongation at Break (%)	104	
Elongation at Yield (%)	6	ASTM D790
Flexural Strength (MPa)	37	
Flexural Modulus (MPa)	990	
Notched Izod Impact Strength (J/m)	55	ASTM D256
Unnotched Izod Impact Strength (J/m)	Did not break	ASTM D4812
Heat Deflection Temperature (°C)		ASTM D648
@ 0.45 MPa	52	
@ 1.82 MPa	43	
Co-efficient of Thermal Expansion (ppm/°C)		ASTM E831
<T _g	91	
>T _g	138	
Glass Transition (T _g)	18	ASTM E1640
Shore Hardness	76D	ASTM D2240
Water Absorption (%)	1.40	ASTM D570

Call: 028 9070 6940

Email: sales@laserproto.com

Web: www.laserproto.com

[Click here to request a quote](#)

Please be advised that all information provided in this document is representative of typical properties and as advised by the material manufacturer. Performance characteristics of these products may vary according to product application, operating conditions or with end use.

Laser Prototypes Ltd makes no warranties of any type, express or implied, with respect to any of the goods or services supplied. This includes but is not limited to any warranty of fitness for a particular purpose or of properties or of suitability for a specific application. Data are subject to change without notice as part of our continuous development and improvement processes.